

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problems Mailbox.**


**THIS PAGE BLANK (USPTO)**



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> : A61L 27/02, 27/56, A61F 2/28	A2	(11) International Publication Number: <b>WO 00/64504</b> (43) International Publication Date: 2 November 2000 (02.11.00)
<p>(21) International Application Number: PCT/SE00/00802</p> <p>(22) International Filing Date: 28 April 2000 (28.04.00)</p> <p>(30) Priority Data: 9901523-2 28 April 1999 (28.04.99) SE</p> <p>(71) Applicant (for all designated States except US): BRUCE MEDICAL AB [SE/SE]; P.O. Box 81, S-260 40 Viken (SE).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): BRUCE, Ingrid [SE/SE]; Strandlyckevägen 35, S-260 40 Viken (SE). BRUCE, Lars [SE/SE]; Strandlyckevägen 35, S-260 40 Viken (SE).</p> <p>(74) Agent: AWAPATENT AB; P.O. Box 5117, S-200 17 Malmö (SE).</p>	<p>(81) Designated States: AE, AG, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, DZ, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (Utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p><b>Published</b> <i>In English translation (filed in Swedish). Without international search report and to be republished upon receipt of that report.</i></p>	

(54) Title: BODY FOR PROVIDING INGROWTH AND GROWTH OF BONE TISSUE AND/OR CONNECTIVE TISSUE AND METHOD OF MAKING SUCH A BODY



## (57) Abstract

A body, such as a grain, for providing ingrowth and growth of bone tissue and/or connective tissue. The body consists of a plastic or non-essentially elastic biocompatible material, preferably metal or metal alloy. It is also porous, having the following porosity characteristics: (a) the porosity is continuous and (b) the opening of cavities/indentations/pockets and the ducts connecting them has the width of > about 50  $\mu\text{m}$  for bone tissue and > about 10  $\mu\text{m}$  for connective tissue. In a method of making such a body, the body has been produced by blowing gas into a melt of metal. An advantageous use of bodies according to the invention is enclosing thereof in a casing, formed with openings, for making an implant, such as a spinal implant.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

BODY FOR PROVIDING INGROWTH AND GROWTH OF BONE  
TISSUE AND/OR CONNECTIVE TISSUE AND METHOD  
OF MAKING SUCH A BODY

SE-B-462,638 discloses a means for fixing an elongate prosthesis, such as the stem of a femoral prosthesis, to living tissue which defines a cavity in which a length of the prosthesis is received with a gap to the  
5 boundary of the cavity. Essentially the entire gap is filled with loose, but packed grains of a biocompatible material, said grains interlocking. As an example of granular material titanium is mentioned, and the grains are stated to be irregular, essentially non-elastic and pre-  
10 ferably porous, the latter property being said to bind growth of bone tissue which has grown from the osseous wall. The porosity has been obtained by blowing gas through a melt of the granular material.

US-A-5,217,496 discloses an implant suited for use  
15 in living bone tissue and comprising a support of titanium having a porous outer surface and an attached layer of a mixture consisting of disintegrated living bone tissue and titanium powder. The mixture is supplied with nutriment which makes the disintegrated bone tissue grow  
20 and form tissue which connects the disintegrated bone tissue and the titanium powder with each other and with the support.

US-A-5,676,700 discloses biocompatible structure elements for repair, reinforcement and replacement of  
25 bone tissue, said elements being indicated to form an osteoconductive or osteoinductive matrix in a bone tissue cavity. The material of the elements can be titanium and the elements are said advantageously to be microporous for ingrowth of natural bone.

30 All the documents above mention as biocompatible material, in addition to titanium, inter alia, hydroxylapatite, bioceramics, bioglass.

In the above documents, porosity of biocompatible materials is thus pointed out to cause something favourable for binding of bone tissue.

According to the invention, it has surprisingly been found that a predetermined measure of the porosity of biocompatible material is in fact a decisive factor as regards the growth rate of bone tissue. It has been found that while surface porosity certainly allows binding of bone tissue, a significantly increased growth rate of bone tissue and a larger amount of bone are obtained and, thus, a significantly improved anchoring and strength of bone tissue on the biocompatible material if

- the body, such as a grain, of the biocompatible material is continuously porous,
- the porosity of the body has a minimum limit value.

An additional advantage of the invention is obtained by the strength of the porous granule with grown-in bone tissue being greater than if bone is not allowed to grow in. Owing to the ingrowth of bone, the strength will mainly be carried by the bone tissue, which is favourable from the biomechanical point of view.

By "continuously porous" is here meant a porosity which allows bone tissue to grow through the porous body, such as the grain of biocompatible material. According to the invention, such porosity results in cavities in the body which are interconnected by ducts, passages, so that growth of bone tissue onto a part of the outer surface of the body allows the growth to continue through the body and out through other parts of the outer surface of the body. By cavity is meant indentations, pits, pockets of an arbitrary shape, and the ducts, passages, interconnecting these cavities can have an arbitrary form and constitute part of the cavities. Examples of such a structure can be found in nature in corals or dripstone caves.

By minimum limit value is here meant an opening of an indentation, pit, pocket and a duct opening having a width of > about 50  $\mu\text{m}$ . A smaller opening dimension restricts or inhibits the growth of bone tissue, probably because the supply of nutriment is inhibited and the bone is prevented from developing its normal structure with the elements that are included. In fact there is no upper limit of the porosity of the body. The upper limit is rather determined by the strength properties of the body.

According to the invention, cavities can be allowed to form of surface pores in bodies which are located next to each other and have open surface pores, so that the surface pores in one body form a cavity or duct/passage with the surface pores in the other body.

According to the invention, it has also been found that a brittle biocompatible material, such as hydroxylapatite, is not optimal for the purposes of the invention when such material is used for repair, reinforcement and replacement of natural bone. Such a material easily decomposes when subjected to a load, which inevitably occurs, for example when the human body or a part of the human body, in which the biocompatible body, such as the grain, is located, is subjected to a load when e.g. the extremities move. Decomposed parts of a body of biocompatible material cause an unfavourable inflammatory reaction which inhibits the formation of bone and which often results in bone resorption.

According to the invention, a metallic material or non-brittle composites are therefore chosen, where natural material, such as hydroxylapatite, bioceramics etc., can be included as a component in the material of the porous body and another component, such as plastic, guarantees plasticity. The body material according to the invention should in fact be plastic or non-essentially elastic. Excessive elasticity causes pressure on the bone tissue, with the ensuing destruction thereof.

Titanium (titanium dioxide) is advantageously selected as metallic material. The porosity of the titanium body is advantageously achieved by blowing gas through a melt of titanium. This makes it possible to  
5 produce titanium grains, as mentioned in SE-B-462,638.

The requirement as to porosity as stated above is, however, not automatically satisfied by blowing gas through a melt of metal. According to the invention, a check is therefore made of the porosity of the body/  
10 grain/grains obtained in this manner to ensure that it/they satisfies/satisfy the requirement. The check can be carried out, for example, by means of fluoroscopy at a suitable wavelength and a TV receiver and automatic separation (e.g. from a conveyor belt) of grains that do not  
15 satisfy the above-mentioned requirement.

The above limit value of  $>$  about  $50\text{ }\mu\text{m}$  relates to bone tissue. If ingrowth of connective tissue is desired instead of or at the expense of bone tissue, the limit value is instead  $>$  about  $50\text{-}10\text{ }\mu\text{m}$ .

20 A porous body, such as a grain, according to the invention can be implanted in a living body, such as a human body, for filling a bone cavity, as replacement, after growth of bone tissue in vivo, a lost leg (rheumatism, osteoporosis) or for fixing a prosthesis according  
25 to SE-B-462,638. A porous body according to the invention can also serve as a base for preculturing of bone tissue in vitro or be filled with a nutrient solution containing, inter alia, growth factors in vitro for subsequent implanting in living tissue. In the case of filling a  
30 bone cavity, it is preferred for the body to be granular and irregular and to have the size  $< 10\text{ mm}$ , so that a plurality of/many grains optimally fill the bone cavity.

The porous body can be filled with a decomposable material, for example of a so-called matrix of the natural material. Examples of such natural matrices are gels  
35 of collagen, fibrin, starch and hyaluronic acid. According to the invention, this matrix is decomposed to be



replaced with the ingrowing bone tissue. The ingrowth of bone tissue can be further stimulated if growth-stimulating substances are added to the decomposable material, above all growth factors such as TGF beta (Transforming Growth Factor beta) or BGF (Bone Growth Factor). The pores in the body according to the invention can be moved with the gel material, e.g. by suction, before the material is ready-gelled.

Smaller bodies, grains according to the invention can be enclosed in a casing, flexible or rigid, for producing an implant. For example, grains according to the invention can be enclosed in a rigid sleeve so as to form, together with the sleeve, a spinal implant, see e.g. the sleeve in US-A-5,015,247. Other possibilities of enclosing in a casing are disclosed in SE 9803078-6. The casing has openings to allow ingrowth and growth of biological cell material to and from the grains, through the casing. Grains according to the invention can be mixed with decomposed biological tissue.

Embodiments of the invention are illustrated in the accompanying Figures which are electron microscope images and of which Fig. 1 shows a porous structure according to the invention and Fig. 2 shows another porous structure according to the invention of the outer surface of a titanium grain. Fig. 3 is an image of a thin section of a titanium grain with porosity according to the invention. All images are made of an irregular grain or granule which has been removed from the femur in a human body after implanting using a vibration technique which is described in more detail in SE-B-462,638.

Fig. 1 shows a structure in the form of a mound of stones and Fig. 2 shows a coral structure. The structures have been provided by blowing gas through a melt of titanium and applying the above-mentioned quality check. Both images show a whitish-grey film of living material, the prestage of bone tissue, which covers the outer surface of the grain and has penetrated into the cavities and

gaps in the pores of the titanium grain. Fig. 1 also shows bone cell growths bridging cavities/gaps in the structure.

Fig. 3 illustrates bone tissue which has intersect-  
5 ed, penetrated a grain according to the invention.

Clinical analyses have proved that the bone tissue in grains according to Figs 1-3 had a composition of 95-98% bone, 2% marrow and 0-3% connective tissue, which essentially corresponds to the composition of the bone  
10 outside the grains in their vicinity.

## CLAIMS

1. A body, such as a grain, for providing ingrowth  
5 and growth of bone tissue and/or connective tissue, said  
body being made of a plastic or non-essentially elastic  
biocompatible material, preferably metal or metal alloy,  
c h a r a c t e r i s e d in that it is porous and  
has the following porosity characteristics:

- 10       - the porosity is continuous  
         - the opening of cavities/indentations/pockets and  
the ducts/passages interconnecting them has a width of  
> about 50  $\mu$ m for bone tissue and > about 10  $\mu$ m for con-  
nective tissue.

15       2. A body as claimed in claim 1, c h a r a c t e r -  
i s e d in that it is made of titanium.

         3. A body as claimed in claim 1 or 2, c h a r a c -  
t e r i s e d in that its cavities are filled with a  
decomposable material, e.g. a matrix of natural material,  
20 such as gel of collagen, fibrin, starch, hyaluronic acid.

         4. A body as claimed in any one of claims 1-3,  
c h a r a c t e r i s e d in that the decomposable mate-  
rial contains growth-stimulating substances.

         5. A body as claimed in any one of claims 1-4,  
25 c h a r a c t e r i s e d in that it has a coral struc-  
ture.

         6. A body as claimed in any one of claims 1-5,  
c h a r a c t e r i s e d in that it is < 10 mm.

         7. A body as claimed in any one of claims 1-6,  
30 c h a r a c t e r i s e d in that it consists of an indi-  
vidual in an aggregate of similar bodies.

         8. A method for making a body as claimed in any one  
of claims 1-7, c h a r a c t e r i s e d by producing  
the body, consisting of metal, such as titanium, by blow-  
35 ing gas through the melt of the metal and separation of  
bodies with the opening of cavities/indentations/pockets

and of the ducts/passages connecting them having the width of  $< 50 \mu\text{m}$ .

9. Use of bodies as claimed in claim 7 in a casing provided with openings/pores, for producing implants.

5        10. Use as claimed in claim 9, wherein the casing is a rigid cylindrical sleeve for producing a spinal implant.




Fig 1

2/3




Fig 2

3/3



Fig 3

**THIS PAGE BLANK (USPTO)**



(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
2 November 2000 (02.11.2000)


PCT

(10) International Publication Number  
**WO 00/64504 A3**

- (51) International Patent Classification<sup>7</sup>: **A61L 27/06**, 27/56, A61F 2/28, 2/44 (74) Agent: AWAPATENT AB; P.O. Box 5117, S-200 17 Malmö (SE).
- (21) International Application Number: PCT/SE00/00802 (81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 28 April 2000 (28.04.2000)
- (25) Filing Language: Swedish
- (26) Publication Language: English
- (30) Priority Data: 9901523-2 28 April 1999 (28.04.1999) SE
- (71) Applicant (*for all designated States except US*): BRUCE MEDICAL AB [SE/SE]; P.O. Box 81, S-260 40 Viken (SE).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): BRUCE, Ingrid [SE/SE]; Strandlyckevägen 35, S-260 40 Viken (SE). BRUCE, Lars [SE/SE]; Strandlyckevägen 35, S-260 40 Viken (SE).
- Published:  
— With international search report.

[Continued on next page]

(54) Title: BODY FOR PROVIDING INGROWTH AND GROWTH OF BONE TISSUE AND/OR CONNECTIVE TISSUE AND METHOD OF MAKING SUCH A BODY



(57) Abstract: A body, such as a grain, for providing ingrowth and growth of bone tissue and/or connective tissue. The body consists of a plastic or non-essentially elastic biocompatible material, preferably metal or metal alloy. It is also porous, having the following porosity characteristics: (a) the porosity is continuous and (b) the opening of cavities/indentations/pockets and the ducts connecting them has the width of > about 50  $\mu\text{m}$  for bone tissue and > about 10  $\mu\text{m}$  for connective tissue. In a method of making such a body, the body has been produced by blowing gas into a melt of metal. An advantageous use of bodies according to the invention is enclosing thereof in a casing, formed with openings, for making an implant, such as a spinal implant.

WO 00/64504 A3



(88) Date of publication of the international search report:  
22 March 2001

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 00/00802

## A. CLASSIFICATION OF SUBJECT MATTER

IPC7: A61L 27/06, A61L 27/56, A61F 2/28, A61F 2/44

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: A61L, A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0856299 A1 (OFFICE NATIONAL D'ETUDES ET DE RECHERCHES AEROSPATIALES), 5 August 1998 (05.08.98), abstract claims --	1-11
A	SE 462638 B (AB IDEA), 6 August 1990 (06.08.90) --	1-10
A	WO 9816267 A1 (COLLEGE DUBLIN), 23 April 1998 (23.04.98), abstract claims 1-4 --	1-11
A	EP 0267624 A2 (ASAHI KOGAKU KOGYO KABUSHIKI KAISHA), 18 May 1988 (18.05.88), abstract claims --	1-11

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

14 July 2000

Date of mailing of the international search report

26 -07- 2000

Name and mailing address of the ISA:

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Ellen Setréus/gh

Telephone No. +46 8 782 25 00

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 00/00802

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 9313815 A1 (LUCOCER AKTIEBOLAG), 22 July 1993 (22.07.93), abstract claim 1 --	1-10
A	WO 9913478 A1 (METAGEN, LLC), 8 April 1999 (08.04.99), abstract claim 1,6, figures 1-5 --	1-11
A	US 4781721 A (HANS GRUNDEI), 1 November 1988 (01.11.88), abstract claim 1 --	1-11
A	WO 9724084 A1 (JOINT-STOCK COMPANY"ALIMITED"), 10 July 1997 (10.07.97), abstract fig 6 --	1-11
A	EP 0159036 A2 (DRAENERT, KLAUS), 23 October 1985 (23.10.85), abstract figures --	1-10
A	US 5645598 A (ROBERT E. BROSNAN III), 7 August 1997 (07.08.97), abstract fig 13 --	10-11
P,X	WO 0013615 A1 (LANKA LIMITED), 16 March 2000 (16.03.00), claim 1-9 --	1-11
P,A	WO 9934845 A1 (BIORTHEX INC. ET AL), 15 July 1999 (15.07.99) -- -----	1-11

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

02/12/99

International application No.

PCT/SE 00/00802

Patent document cited in search report			Publication date	Patent family member(s)		Publication date
EP	0856299	A1	05/08/98	EP	0907520 A	14/04/99
				FR	2758974 A,B	07/08/98
SE	462638	B	06/08/90	AT	84407 T	15/01/93
				AT	101998 T	15/03/94
				AU	611900 B	27/06/91
				AU	1571288 A	02/11/88
				CA	1327099 A	22/02/94
				CN	1024751 B	01/06/94
				DE	3877570 A	25/02/93
				DE	3888214 D,T	30/06/94
				DK	165727 B,C	11/01/93
				DK	585588 A	25/11/88
				EP	0353241 A,B	07/02/90
				SE	0353241 T3	
				EP	0501595 A,B	02/09/92
				SE	0501595 T3	
				ES	2006874 A	16/05/89
				FI	93168 B,C	30/11/94
				FI	894623 A	29/09/89
				JP	2503273 T	11/10/90
				JP	2561337 B	04/12/96
				KR	9707085 B	02/05/97
				MX	171297 B	18/10/93
				NO	885325 A	29/11/88
				SE	8701313 A	01/10/88
				US	5015256 A	14/05/91
				WO	8807355 A	06/10/88
WO	9816267	A1	23/04/98	AU	4636297 A	11/05/98
EP	0267624	A2	18/05/88	JP	1049501 B	25/10/89
				JP	63125259 A	28/05/88
WO	9313815	A1	22/07/93	AU	3269993 A	03/08/93
				CZ	9301643 A	16/02/94
				EP	0623031 A	09/11/94
				FI	933532 A	10/08/93
				JP	7506732 T	27/07/95
				NO	932844 A	08/10/93
				SE	469653 B,C	16/08/93
				SE	9200072 A	14/07/93
				US	5464440 A	07/11/95
WO	9913478	A1	08/04/99	AU	9083298 A	29/03/99
				EP	0937303 A	25/08/99
				GB	9719253 D	00/00/00
US	4781721	A	01/11/88	CH	660122 A,B	31/03/87
				DE	3106917 A,C	25/11/82
				DE	8105177 U	12/01/84
				FR	2500297 A,B	27/08/82
				GB	2093701 A,B	08/09/82
				JP	57148943 A	14/09/82
WO	9724084	A1	10/07/97	NONE		

# INTERNATIONAL SEARCH REPORT

Information on patent family members

02/12/99

International application No.

PCT/SE 00/00802

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0159036 A2	23/10/85	SE 0159036 T3	
		AT 79009 T	15/08/92
		DE 3414924 A	31/10/85
		DE 3586438 A	10/09/92
		JP 1840105 C	25/04/94
		JP 5052225 B	04/08/93
		JP 61033660 A	17/02/86
		US 4713076 A	15/12/87
US 5645598 A	07/08/97	AU 1748297 A	11/08/97
		WO 9725946 A	24/07/97
		US 5766253 A	16/06/98
WO 0013615 A1	16/03/00	NONE	
WO 9934845 A1	15/07/99	AU 1865999 A	26/07/99